



TEST DATA SHEET OF GREEN RUBBER PROCESS OIL 15

DESCRIPTION	TEST UNIT	RESULT	TEST METHOD
VISCOSITY @ 100	°C	15 c.st	ASTMD 445
VISCOSITY @ 40	°C	300 c.st	ASTMD 445
A.P	°C	120 °C	ASTM D 611
F.P.T	°C	170 °C	ASTM D 92
DN@ 15 °C	°C	0.89 g/cm3	ASTM D 4052
PCA	°C	<3%	-

Application

Green Rubber process oil is used in industry ink formulations, isolation manufacturers, automobile tire making factory, rubber manufacturer, shoes, flooring, cable and any other industrial interface.

Packing

Green Rubber Process Oil packed in new or used 200 kg drums, iso tank , flexi tanks and bulk shipments. Each 20 foot container takes 80 drums.

Pub-ltd

No42, 4th Floor, Sepehr Building, Bahonar Street, Isfahan, Iran

- Tel: +98-3133458785
- Fax: +98-3133458781
- Website: www.globallybitumen.com www.pub-ltd.com
- E_mails : info@globallybitumen.com info@pub-ltd.com